CYTEC

Technology ahead of its time™

www.cytec.com

CYPHOS® IL 102

Phosphonium Ionic Liquid



Introduction:

Why consider a "phosphonium" ionic liquid?

Soon after the discovery that certain nitrogen based room temperature liquid salts were found to be useful as battery electrolytes (1a,1b,), interest in these and similar salts as novel fluids and solvents developed. There were a scant number of papers during the 1980s and early 1990s but mainly due to the efforts of the group at The Queen's University – Belfast, headed up by Professor Ken Seddon, there has been an exponential rise in interest and number of publications in the last 7 to 8 years. (2) Indeed, almost an entire issue of Green Chemistry (3) has been devoted to ionic liquids.

Perhaps one of the most influential publications to direct industrial attention to ionic liquids was a feature article entitled "Designer Solvents" in C&E News – March 30,1998 in which Ken Seddon, Robin Rogers, Tom Welton, Helene Olivier and others elaborated on the potential of ionic liquids. While the article dealt almost entirely with nitrogen based ionic liquids, there was a brief reference by Ken Seddon which alluded to the fact that phosphonium salts are also a potential source of numerous ionic liquids. This brief reference to phosphonium ionic liquids is very much representative of the current fraction of publications relating to phosphonium based ionic liquids. With the exception of several papers and patents by George Parshall in the mid 1970s using stannate and germanate salts and John Knifton et al in the early 1990s which centre on the use of molten tetrabutylphosphonium bromide as an ionic solvent, almost the entire volume of ionic liquid literature deals with nitrogen based systems and in particular, those based on 2-methylimidazolium salts.

There was a good reason for the lack of phosphonium based ionic liquid publications – availability of the starting material! While Cytec has been commercially producing phosphine derivatives since 1971, it was not until 1990 that tributylphosphine was produced on a large commercial scale. Since that time, not only has tetrabutylphosphonium chloride and bromide become available in multi ton scales, many other trialkylphosphines and the corresponding quaternary phosphonium salts are or can be manufactured on a large scale.

The phosphonium cation contains four substituents and the various combinations along with the multitude of various available anions represents an enormous number of possible salts. Even when one restricts the cation to the generic formula – $[PR_3R']^+$, the number is still very large. Of course, not all such phosphonium salts are liquid at room temperature, but by a judicious selection of R and R' as well as the appropriate anion, there are many phosphonium salts which are in fact liquid at room temperature and many more which fall within the broad general definition of ionic liquids as salts which are low melting – that is less than 100 °C.

There are several reasons why one might consider a phosphonium ionic liquid. The most important one for those contemplating an industrial process is availability and cost. Phosphonium salts can meet both of these demands – already Cytec is manufacturing phosphonium salts on a multi ton scale and because of the high volumes, costs will be relatively low. For commercial products, chemical inventory registration is also part of the availability equation. While, most of the possible phosphonium ionic

liquids are still not registered, several are already listed on EINECS, TSCA, EEC, AICS, PICCS and DSL.

Ionic liquids, in general, are not going to be outrageously expensive, but they will not be in the same league as toluene, 2-hydroxypropane (IPA) or tetrahydrofuran (THF). This means that to be economically viable, they must be chemically as well as thermally very stable for multiple recycle use. Even 0.5 to 1% decomposition can lead to major losses after 10 to 20 cycles. Not only will there be solvent losses but there will also be contamination of the ionic liquid solvent and/or products with decomposition byproducts.

In this regard, phosphonium salts are much more thermally stable than the corresponding ammonium salts and even have an edge on imidazolium salts. This is very important for processes which operate at temperatures greater than 100 °C. In addition to being slightly less thermally stable, the imidazolium cation contains protons which are not entirely inert. They are some what acidic which can result in carbene formation. Phosphonium salts, on the other hand have no such acidic protons.

The fact that alkylphosphonium salts are, in general, less dense than water can be beneficial in product work-up steps while decanting aqueous streams which contain inorganic salt byproducts. Imidazolium salts, on the other hand are more dense than water.

Trade Name: **CYPHOS IL 102 phosphonium ionic liquid**

Chemical Name: tetradecyl(trihexyl)phosphonium bromide

C.A.S. Number: None

Registration: None



Density and Miscibility:

CYPHOS IL 102 phosphonium ionic liquid is a slightly viscous room temperature ionic liquid. It is less dense than water (Figure 1), is colorless to pale yellow and is immiscible with water although it is sparingly soluble in water and can dissolve up to 8% water. When dry, it is totally miscible with a wide range of organic solvents such as indicated in Table 1

Table 1

CYPHOS IL 102 Miscibility

Diluent	**Miscible**
water	No
hexane	Yes
toluene	Yes
2-hydroxypropane (IPA)	Yes
diethylether	Yes
tetrahydrofuran	Yes
dichloromethane	Yes

CYPHOS IL 102 has unique miscibility properties which can be utilized to separate organic products from metal catalysts and byproduct inorganic salts. When dry, it is totally miscible with non polar solvents such as hexane, however when an excess of water is added to the system, three liquid phases form. The upper phase is essentially hexane which can contain the organic reaction product. The middle layer is CYPHOS IL 102 saturated with water and will contain any metal/ligand catalyst. The lower layer is essentially water but will contain any byproduct inorganic salts (4, Figure 2).

When fully saturated, CYPHOS IL 102 will contain 4.5% water. This is considerably less than the corresponding chloride salt – CYPHOS IL 101. The latter, when saturated will dissolve up to 14.0% water.

Thermal Stability:

Literature reports of ionic liquid thermal stabilities using standard TGA conditions – that is heating a sample at 5 to 10 °C per minute under an inert atmosphere such as nitrogen or under oxidizing conditions such as under an air atmosphere will indicate unduly high thermal stabilities – even in excess of 300 °C. However, the true thermal stability of such salts is best determined under isothermal conditions – that is heating a sample rapidly to the test temperature and then observing the weight loss over time. Figures 3 and 4 contain weight loss changes with time over several temperatures under air and dinitrogen atmospheres. It would appear that safe operating temperatures for CYPHOS IL 102 under air and nitrogen will be approximately 150 °C and 180 °C.

CYPHOS IL 102 appears to be slightly more stable than the corresponding chloride salt – CYPHOS IL 101 and like all phosphonium salts, it is much more thermally stable than ammonium halide salts (Figure 5) and even significantly more stable than imidazolium halides (Figure 6).

Applications:

Although there are many potential applications for CYPHOS IL 102, like CYPHOS IL 101, it is especially recommended for palladium catalyzed Suzuki and Heck coupling reactions (7, 8). Both authors have demonstrated that such catalyst/solvent systems can be recycled with fresh substrate without loss of activity.

The stability of phosphonium ionic liquids under highly reducing conditions has been demonstrated by Clyburne et al (9). Here CYPHOS IL 101 remains inert as it is used as a solvent to electrochemically and chemically reduce the imidazolium cation to a carbene. This has implications for using phosphonium ionic liquids in highly reductive environments. For example in a more recent paper (10), Clyburne et. al. have demonstrated the compatibility of commercial Grignard reagents in phosphonium ionic liquids such as CYPHOS IL 101. Consequently they were able to convert phenylmagnesium bromide to biphenyl, benzaldehyde, benzyl alcohol, bromobenzene and dimethylbenzyl alcohol in CYPHOS IL 101. The products were readily isolated after adding water and hexane which formed three liquid phases. The products partitioned into the upper hexane layer while the magnesium salts were directed to the lower aqueous phase. In the same paper, they also reported an equally successful $NaBH_4$ reduction of benzaldehyde. Benzyl alcohol was the only detectable product. While the above reactions

were carried out in CYPHOS IL 101, there is no reason to believe that they could not be carried out in CYPHOS IL 102 as well.

Ionic Liquid Intermediate:

With the addition of $AlCl_3$ or transition metal salts such as $FeCl_3$, $TiCl_3$ or $CuCl_2$, various tetradecyl(tributyl)phosphonium ionic liquids with complex metal halide anions can be formed. Using the proper solvent (usually water) the chloride anion can be converted via metathesis to hexafluorophosphate, tetrafluoroborate, triflate, bistriflamide or almost any other cation provided the free acid or alkali metal salt is available. (5, 6)

Analysis:

CYPHOS IL 102 typically assays 96 to 97% $[PR_3R']^+Br^-$ (R = hexyl and R' = tetradecyl). However, the product will also contain traces (0 .1 to .4 %) of tetradecene isomers, 0.1 to 0.5% HBr and 0.1 to 1.2% $[PR_3H]^+ Br^-$. Titration with standardized $AgNO_3$ in a 75% aqueous 2-hydroxypropane (IPA) solvent will yield the total chloride content. This result when combined with a corresponding NaOH titration will yield the $[PR_3H]^+ Cl^-$, HBr and $[PR_3H]^+ Br^-$ content. The volatile content (tetradecene isomers) are determined by an internal standard G.C. analysis of an octane extract.

^{31}P NMR is generally not suitable for precise analysis. However, the distinctive signal at +33 ppm can be useful for qualitative analysis.

While electrospray mass spectral analysis (ESMS) is generally not available in every laboratory, this also a very useful tool for both quantitative and qualitative analysis.

References:

1a) Fannin, A .A, Jr; King, L. A.; Levisky, J. A.; Wilkes, J. S.; J. Phys. Chem., 1984, **88**, 2610-2614

1b Fannin, A. A. Jr; Floreani, D. A.; King, L. A.; Landers, J. S.; Piersma, B. J.; Stech, D. J.; Vaughn, R. L.; Wilkes, J. S.; and Williams, J. L., J. Phys. Chem. 1984, **88**, 2614-2621

2) "Forward", Professor Ken Seddon, Green Chemistry April, 2002.

3) Green Chemistry April, 2002

4) WO 03/020843 A1 "Composition Comprising Phosphonium Salts and Their Use" ; A Ramani, K Seddon, C Hardacre, M Earle A Robertson

5) "Industrial Preparation of Phosphonium Ionic Liquids"; Christine Bradaric, Andrew Downard, Christine Kennedy, Allan Robertson, Yuehui Zhou; Green Chemistry, 2003, **5**, 143-152

6) WO 01/87900 A1 "Phosphonium Salts"; A Robertson

7) "Molten salts as an efficient medium for palladium-catalyzed C-C coupling reactions"; Kaufmann, Dieter E.; Nouroozian, Mahmoud; Henze, Heiko; Synlett (1996), **11** , 1091-1092

8) "Suzuki cross-coupling reactions of aryl halides in phosphonium salt ionic liquid under mild conditions" ; McNulty, James; Capretta, Alfredo; Wilson, Jeff; Dyck, Jeff; Adjabeng ; Chemical Communications (Cambridge, United Kingdom) (2002), **17**,1986-1987.

9) "Electrochemical reduction of an imidazolium cation: a convenient preparation of imidazol-2-ylidenes and their observation in an ionic liquid"; Chem. Commun.,2004,1972-1973; B. Gorodetsky, T. Ramnial, N. Branda and J. Clyburne

10) "Phosphonium ionic liquids as reaction media for strong bases"; Chem. Commun., 2005,327-327; T Ramnial, D D Ino and J Clyburne

Figure 1

CYPHOS IL 102 – Density vs. Temperature



Figure 2

CYPHOS IL 102 - Product Recovery & Catalyst/IL Recycle



Figure 3

CYPHOS IL 102 – Isothermal TGA Plots under Air



Figure 4

CYPHOS IL 102 – Isothermal TGA Plots under N_2



Figure 5

Tetrahexylammonium chloride – Isothermal TGA Plot under N_2



Figure 6

$[bmim]^+ Cl^-$ - Isothermal TGAPlot under N_2



Important Notice: The information and statements in this data sheet are believed to be reliable but are not to be construed as a warranty or representation for which we assume legal responsibility or as an assumption of a duty on our part. Users should undertake sufficient verification and testing to determine the suitability for their own particular purpose of and information or products or vendors referred to within. NO WARRANTY OF FITTNESS FOR A PARTICULAR PURPOSE IS MADE. Nothing in this data sheet is to be taken as permission, inducement or recommendation to practice any patented invention without a license.

Trademark Notice: The ® indicates a Registered Trademark in the United States and the TM or * indicates a Trademark in the United States. The mark may also be registered, the subject of an application for registration or a trademark in other countries.

Last updated: September 2, 2005