

# Raylok™ 5022

## Technical Data Sheet

1 / 2

*UV curable performance product for electrical sleeves coatings*

### INTRODUCTION

Raylok 5022 is an UV curable high performance solution for **electrical sleeves coatings**. Raylok 5022 is based on a special aromatic urethane acrylate diluted with around 12% of dipropylene glycol diacrylate (DPGDA)<sup>(1)</sup> monomer. Raylok 5022 exhibits good cured properties under ultraviolet light (UV) because it contains some photoinitiators. Cured films based on Raylok 5022 show excellent flexibility, electrical and thermal insulating properties, and are especially suited for **automotive applications**.

### PERFORMANCE HIGHLIGHTS

Raylok 5022 is characterized by :

- light colour
- high viscosity

UV/EB cured coatings based on Raylok 5022 are characterized by the following performances :

- **excellent flexibility**
- **excellent electrical insulation**
- **very good thermal ageing**
- **very good chemical resistance**

The properties of Raylok 5022 are excellent. These properties may decrease by the introduction of other formulation components, such as reactive diluent(s) or other additives.

### SUGGESTED APPLICATIONS

Raylok 5022 is recommended for use in

- clear coatings where excellent flexibility and electrical insulating properties are required
- sleeving glass fiber tubes used especially in the automotive industry.

### TYPICAL VALUES

Höppler viscosity at 60°C, mPa.s	~ 8000
Colour, Gardner	2 max.
Appearance :	normally crystalline but cloudy high viscous liquid aspect in summer.
Tg	- 43°C
Tm (range)	25 – 40°C

### PHYSICAL PROPERTIES

Density, g/cm <sup>3</sup>	1.14
Polymer solids, % by weight	100
DPGDA, % by weight	~ 12

### VISCOSITY REDUCTION

**Raylok 5022 needs to be applied at 60-70°C due to its high viscosity, without further dilution.** The addition of diluting acrylates such as tripropyleneglycol diacrylate (TPGDA)<sup>(1)</sup>, 1,6 hexanediol diacrylate (HDDA)<sup>(1)</sup> or dipropylene glycol diacrylate (DPGDA) will strongly reduce the mechanical properties of the coating and increase the hardness.

Cytec Surface Specialties S.A./N.V. Anderlechtstraat 33, B-1620, Drogenbos, Belgium

Telephone: ++32 (0)2 334 51 11

E-mail: [tsd.radcure@cytec.com](mailto:tsd.radcure@cytec.com)

Web Site: [www.surfacepecialties.com](http://www.surfacepecialties.com)

**Disclaimer:** Cytec Surface Specialties S.A./N.V. or any of its affiliated companies (hereinafter "Cytec Surface Specialties") decline any liability with respect to the use made by any third party of the information contained herein. The information contained herein represents Cytec Surface Specialties' best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Cytec Surface Specialties is the sole owner or authorized user of the intellectual property rights relating to the information communicated. The information relating to the use of the products is given for information purposes only. No guarantee or warranty is provided that the product is adapted to the client's specific use. The client should perform its own tests to determine the suitability for a particular purpose. The final choice of use of a product remains the sole responsibility of the client. <sup>TM</sup> trademark of Cytec Surface Specialties Group.

# Raylok™ 5022

## Technical Data Sheet

2 / 2

*UV curable performance product for electrical sleeves coatings*

**The UV curing process increases the production speed by a factor of 10 compared to the conventional solvent-borne systems and on top of that is VOC-free.**

We recommend an UV oven with two UV lamps in front of each other in order to get the same UV curing and limit the shrinkage.

### **Elongation at break**

Raylok 5022 shows an important improvement vs. existing materials for the same application :

Raylok 5022	85 – 95 % elongation
IRR 281	80 – 90 % elongation

<sup>(1)</sup> TPGDA, HDDA and DPGDA are produced by Cytec Surface Specialties.

### **STORAGE AND HANDLING**

Care should be taken not to expose radiation curable products to temperatures exceeding 40°C for prolonged periods or to direct sunlight. This might cause uncontrollable polymerization of the product with generation of heat.

The product is highly light sensitive.

Storage and handling should be in stainless steel, amber glass, amber polyethylene or baked phenolic lined containers. Do not store this material under an oxygen free atmosphere. Use dry air to displace material removed from the container. This material should not be stored for more than 6 months.

### **PRECAUTIONS**

The following is a summary of the precautions to be taken when handling this product. Please refer to the Safety Data Sheet for further details. The toxicological properties of this material have not been fully determined. Products of this type can be expected to be eye and skin irritant and have the potential to cause sensitization or other allergic responses. Appropriate precautions should be taken to avoid eye and skin contact and to avoid inhalation of the aerosols or vapours. Consult the relevant Safety Data Sheet for appropriate handling procedures and protective equipment prior to using this or any other material referred to in this bulletin.

See Safety Data Sheet for emergency and first aid procedure.

### **STATUTORY LABELLING**

Please refer to Safety Data Sheet.

January 2008 - Supersedes previous versions

<b>Cytec Surface Specialties S.A./N.V. Anderlechtstraat 33, B-1620, Drogenbos, Belgium</b>		
<b>Telephone:</b> ++32 (0)2 334 51 11	<b>E-mail:</b> tsd.radcure@cytec.com	<b>Web Site:</b> www.surfacepecialties.com

**Disclaimer:** Cytec Surface Specialties S.A./N.V. or any of its affiliated companies (hereinafter "Cytec Surface Specialties") decline any liability with respect to the use made by any third party of the information contained herein. The information contained herein represents Cytec Surface Specialties' best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Cytec Surface Specialties is the sole owner or authorized user of the intellectual property rights relating to the information communicated. The information relating to the use of the products is given for information purposes only. No guarantee or warranty is provided that the product is adapted to the client's specific use. The client should perform its own tests to determine the suitability for a particular purpose. The final choice of use of a product remains the sole responsibility of the client. <sup>TM</sup> trademark of Cytec Surface Specialties Group.